High index glass beads

1) Glass Beads with Refractive Index 1.93nd


1.93Nd glass bead is used for "Exposed-Lens" type retro-reflective articles(refer to enclosed glossary), such as open-type reflective sheets, reflective fabric. reflective tape, reflective yarn and "En capsulated-Lens" type retro-reflective articles(refer to enclosed glossary), such as high intensity grade reflective sheet.

I. Technical Data

Composition	TiO ₂ -BaO-SiO ₂ GLASS
Refractive Index	1.93±0.01Nd
Specific Gravity	4.1±0.2 g/cm ³
Color	White
Form	Fine spheres powder
Size	10-100um(can be provided by specific request)
Roundness	≥95%
Opacity	≤1%
	I .

II. Package: 25kg / iron barrel (Volume: 28cm x 23cm), lined with two plastic bags, and

one dryer placed in.
Net Weight: 25kg/barrel
Gross Weight: 26.7kg/barrel





2) Glass Beads with Refractive Index 2.2nd

2.2nd glass bead is used for "Enclosed-Lens" type retro-reflective articles(refer to enclosed glossary), such as engineering grade sheet and super engineering grade sheet which contribute to road signs and traffic safety.

I. Technical Data

Room 1014, 10th Floor, Unit 1, Building 2, New World Centre, Guangyang District, Langfang City, Hebei, China

Tel: 86-316-2013621 Fax: 86-316-7018536

Email: sales@cnglassbead.com Skype: Ifwlfox@hotmail.com

www.cnglassbead.com www.iolan.net

Composition	TiO₂-BaO-ZnO GLASS
Refractive Index	2.2±0.1Nd
Specific Gravity	4.5±0.2 g/cm ³
Color	White
Form	Fine spheres powder
Size	10-100um(can be provided by specific request)
Roundness	≥95%
Opacity	≤5%



II. Package: 25kg / iron barrel (Volume: 28cm x 23cm), lined with two plastic bags,

and one dryer placed in.

Net Weight: 25kg/barrel

Gross Weight: 26.7kg/barrel

III.Storage: Dry and sheltered





3) Aluminum Coated Glass Beads with Refractive Index 1.93nd

Aluminum coated glass bead is used for road signs , traffic safety goods and reflective printing ink.,screen printing etc.

I. Technical Data

Room 1014, 10th Floor, Unit 1, Building 2, New World Centre, Guangyang District, Langfang City, Hebei, China

Tel: 86-316-2013621 Fax: 86-316-7018536

www.cnglassbead.com www.iolan.net

Composition	TiO ₂ -BaO-SiO ₂ GLASS
Refractive Index	1.93±0.01Nd
Specific Gravity	4.1±0.2 g/cm ³
Color	Silver grey
Form	Fine spheres Semi-coated with aluminum
Size	10-100um(can be provided by specific request);



II. Package: 25kg / iron barrel (Volume: 28cm x 23cm), lined with two plastic bags,

and one dryer placed in.

Net Weight: 25kg/barrel

Gross Weight: 26.7kg/barrel

III.Storage: Dry and sheltered

